

Technical Data Sheet

KALDET Transparent Wood Stain No. 270



Application range	For interior solid wood, veneers, and Multiplex boards, also for cabinet interiors, garden furniture. Not suitable for walking areas.																
Technical qualities	Complies with German Industrial Norm (DIN) 53 160, fast to perspiration and saliva. Suitable for toys according to DIN EN 71, part 3. Does not contain protection against blue-staining fungi. KALDET – Transparent Wood Stain No. 270 was rated as very good in the magazine "Öko-Test: Guide for Construction, Habitation, Renovation" edition 5 / 2003.																
Full declaration	Linseed oil - stand oil - natural resin ester, linseed oil, titan dioxide, mineral pigments, chalk, linseed oil - stand oil, castor oil – stand oil, dehydrated castor oil, soya lecithin, linseed oil – wood oil – stand oil, silicic acid, micronized wax, orange oil, pine oil, Isoaliphates, alumina, dehydrated amino sugar, and drying agents free of lead (Co, Mn, Zr, Ca). Without orange oil: 002 clear, 012 spruce, 022 boxwood, 032 pine, 052 brazil, 076 oak, 113 green, 122 ultramarine blue, 124 country blue, 202 white, 203 light.																
Colors	<table><tr><td>002 clear</td><td>042 dark teak</td><td>082 rosewood</td><td>124 country blue</td></tr><tr><td>012 spruce</td><td>052 brazil</td><td>102 ebony</td><td>202 white</td></tr><tr><td>022 boxwood</td><td>062 walnut</td><td>113 green</td><td>203 light</td></tr><tr><td>032 pine</td><td>076 oak</td><td>122 ultramarine blue</td><td>212 light grey</td></tr></table> <p>All colors are inter-mixable. All colors without orange oil comply with the criteria of LIVOS Neutral products for the allergy-prone and chemically sensitive.</p>	002 clear	042 dark teak	082 rosewood	124 country blue	012 spruce	052 brazil	102 ebony	202 white	022 boxwood	062 walnut	113 green	203 light	032 pine	076 oak	122 ultramarine blue	212 light grey
002 clear	042 dark teak	082 rosewood	124 country blue														
012 spruce	052 brazil	102 ebony	202 white														
022 boxwood	062 walnut	113 green	203 light														
032 pine	076 oak	122 ultramarine blue	212 light grey														
Dilution	With SVALOS Spray Thinner No. 293 or SVALOS Thinner No. 222																
Application method	By painting (undiluted), spraying (5 to 10% dilution) or dipping (up to 20% dilution) at temperatures above 12 °C (54 °F) and in dry weather conditions. At higher temperatures, please consider shorter drying times and re-brush sooner.																
Coverage	1 undiluted liter (1.06 quart) is sufficient for approximately 15 to 30 m ² (161 to 323 ft ²), i.e. 44ml/m ² . Could be considerably less, depending on the surface condition and the absorbency of the wood. Test coat recommended!																
Drying time	At 23 °C (73°F) and 50 % relative humidity 12 –24 hours. Subsequent coats can be applied after approximately 24 hours. Provide good light and ventilation conditions during drying times.																
Cleaning	Clean equipment immediately after use with SVALOS Thinner No. 222, or LEVO Brush Cleaner No. 997.																
Specific gravity	Approximately 0.90 g/ml, depending on the color.																
Safety advice	<p>Ensure good ventilation during and after application. Always be sure to store and then dispose of cleaning cloths, polishing pads, sponges, etc. that are still wet or even slightly moist with KUNOS Transparent Wood Stain No. 270 in an airtight metal container or in water, as there is a danger of spontaneous combustion caused by the plant oil content.</p> <p>The product itself will not combust spontaneously.</p> <p>P102 Keep out of reach of children. P301+P310 IF SWALLOWED: Rinse mouth. Do NOT induce vomiting. Immediately call a doctor. EUH066 Repeated exposure may cause skin dryness or cracking. EUH208 Contains limonene, Cobalt (2+) salts. Can cause allergic reactions.</p>																
Disposal	According to locally regulated laws.																
Container sizes	0.375 l; 0.75 l; 2.5 l; 10 l; 30 l.																
Storage	Cool and dry. Shelf life: unopened at least 4 years. Stains in opened containers react with oxygen. The less stain is still there, even more so. Residues should be transferred into smaller containers. See reverse for application instructions.																

How to use

KALDET Transparent Wood Stain No. 270

Preparation	Surface must be dry (wood moisture content below 15%), solid, finely sanded (180 grain), absorbent, clean and free of resin and dust. The moisture content of coniferous wood and tropical deciduous wood should not be higher than 15%; for European deciduous wood the moisture content should not exceed 12%.
Interior wood:	Prime with DUBNO Penetrating Priming Oil No. 261, remove any excess oil after 20 minutes. After drying intermediate sanding. Afterwards, depending on the area of application and the degree of protection needed, 1 to 3 applications. Re-brush the surface 5 to 15 minutes after each application. Please, pay attention to the drying times!
Cabinet interiors Multiplex, veneer, glued wood (interior)	Follow the preparation instructions: see above. Depending on use of the surface 1 – 2 sparing coats with KALDET Transparent Wood Stain No. 270, without priming with DUBNO Penetrating Priming Oil No. 261!
Boxes for bees	Prime with DUBNO Penetrating Priming Oil No. 262 (without orange oil) and apply three times KALDET Transparent Wood Stain No. 270 without orange oil (022 boxwood, 032 pine, 052 brazil, 076 oak, 113 green, 122 ultramarine blue, and 124 country blue).
Important tips	<p>Always do a test application first. Stir thoroughly before use.</p> <p>When purchasing several container of colored wood stain, pay attention to the same batch number.</p> <p>Remove possible skin formed on surface. Provide good ventilation during application and drying times.</p> <p>Seams of new windows should be treated with a single, very thin coat of KALDET No. 270 after priming. Silicone sealant should be applied only after complete drying, and should not be painted over with KALDET No. 270. Linseed oil based putty can be painted over after one day.</p> <p>The use of wax over a colored stain can cause the color to lighten slightly.</p> <p>The colors white and light grey can yellow (yellowing due to the linseed oil) in low light conditions (little daylight). The colors white and light grey should not be painted over with KALDET Transparent Wood Stain “clear” or any other LIVOS oil, as the surface may yellow. Some mixed colors with ultramarine blue and country blue tend to “wash-out” the pigments, which can be eliminated by constant stirring. 10 minutes after application, i.e. re-brush after briefly drying.</p> <p>Colors green (No. 113), ultramarine blue (No. 122) and country blue (No. 124) are getting brownish by reworking with colorless oil.</p> <p>Use color light (203) only as a primer to avoid strong accentuation of the wood grain when the coating will be continued with KUNOS Natural Oil Sealer No. 244.</p> <p>If the stain drips off or bubbles appear during application, an incompatibility exists through the pre-treatment or it has been sanded to smooth. Coarser sanding may possibly create remedy.</p> <p>Exterior wood: KALDET Transparent Wood Stain No. 270 is a thin-layer stain. All colors except clear (002), 012 spruce, white (202) as well as light (203) are suitable for exterior usage; however, a lower UV resistance compared with KALDET All Weather Stain No. 281 should be noted. For priming please note ADAO External Primer No. 259 for wood prone to blue-staining fungi, LINUS Penetrating Oak Priming Oil No. 233 for oak and DUBNO Penetrating Priming Oil No. 261 for tropical wood.</p>

These directions are the result of long years of research and practical testing. They are backed by our most current expert information. New findings may invalidate this information. The latest version is available on our website at www.livos.de. This data sheet is meant to serve as information and instruction. No legal liability should be interpreted from it. In case of doubt, please contact the retailer, wholesaler, or manufacturer.

August 2015