

## Technical Data Sheet

# KALDET All Weather Stain No. 281

<b>Application range</b>	For the treatment of all exterior solid timber. In the interior only for windows. Not suitable for balcony floors or other walking areas.			
<b>Technical qualities</b>	Reinforces and deepens the natural color of the wood grain. After 3 coats water-repellent, weather resistant, and permeable to water vapor. Complies with the German Industrial Norm DIN 53 160, fast to perspiration and saliva. Suitable for toys according to DIN EN 71 part 3. The product does not contain protection against blue-staining fungi.			
<b>Full declaration</b>	Depending on the color: Isoaliphates, linseed oil - stand oil - natural resin ester, wood oil, castor oil - natural resin ester, linseed oil, wood oil - stand oil, linseed oil - stand oil, linseed oil - wood oil - stand oil, mineral pigments, micronized wax, silicic acid, dehydrated amino sugar, soy lecithin, titan dioxide, orange oil, and drying agents free of lead (Ca, Co, Zr, Zn).			
<b>Colors</b>	022 boxtree 032 pine 042 dark teak 052 brazil	054 mahogany 062 walnut 076 oak	082 rosewood 102 ebony 113 green	122 ultramarine blue 124 country blue 212 light grey
	All colors are intermixable.			
<b>Dilution</b>	With SVALOS Thinner No. 222 or SVALOS Spray Thinner No. 293.			
<b>Application method</b>	3 applications by painting (undiluted), spraying (up to 10% dilution) or dipping (up to 20 % dilution) at temperatures above 12°C (54°F) and dry weather conditions.			
<b>Coverage</b>	1 liter (1.06 quart) is sufficient for approximately 15 to 30 m <sup>2</sup> (161 to 323 ft <sup>2</sup> ) per coat, i.e. 44ml/m <sup>2</sup> . Coverage could be considerably less, depending on the condition and the absorbency of the wood. Test application!			
<b>Drying time</b>	At 23°C (73°F) and 50 % relative humidity 12 to 24 hours. Subsequent coats can be applied after approximately 24 hours. Avoid drying delays by providing sufficient light and ventilation during drying times. At higher temperatures, consider shorter drying times, at lower temperatures and higher humidity, please consider longer drying times as given above.			
<b>Cleaning</b>	Clean equipment immediately after use with SVALOS Thinner No. 222 or LEVO Brush Cleaner No. 997.			
<b>Specific gravity</b>	Approximately 0.90 g/ml, depending on the color.			
<b>Safety advice</b>	<p>Ensure good ventilation during and after application. Always make sure, that cleaning cloths, polishing pads, sponges, etc. which are still wet or even slightly moist with KALDET All Weather Stain No. 281, to store and dispose of in an airtight metal container or in water, otherwise there is a danger of spontaneous combustion caused by the plant oil content.</p> <p>The product itself will not combust spontaneously.</p> <p>P102 Keep out of reach of children.  P301+P310 IF SWALLOWED: Rinse mouth. Do NOT induce vomiting. Immediately call a doctor.  EUH066 Repeated exposure may cause skin dryness or cracking.  EUH208 Contains Cobalt (2+) salts. Can cause allergic reactions.</p>			
<b>Disposal</b>	According to local official regulations.			
<b>Container sizes</b>	0.375 l; 0.75 l; 2.5 l; 10 l; 30 l.			
<b>Storage</b>	Cool and dry. Shelf life: unopened at least 4 years. Transfer unused product into a smaller container for storage in order to minimize excess air.			

How to use

# KALDET All Weather Stain No. 281

<b>Preparation</b>	Surface must be dry (wood moisture content below 15%), solid, finely sanded (180 grain), absorbent, and free of resin and dust. For windows and other dimensionally stable wood, the moisture content for coniferous wood and tropical deciduous wood should be below 15% and not exceed 12% in indigenous deciduous wood. Prime with ADAO External Primer No. 259 or LINUS Penetrating Oak Priming Oil No. 233 for oak, one sated or sparing coat depending on the absorbency of the wood. Remove excess oil after 20 minutes. Sand in-between.
<b>Application</b>	Stir thoroughly before use. Remove possible skin formed on surface. Always do a test application first! Apply three coats of KALDET All Weather Stain No. 281 within four weeks. With the second coat, there must be a layer formation. Please note that the formation of running drips on the surface indicates that the coat is too thick, excess product must be removed or spread immediately. After 10 – 30 minutes the coat has to be smoothed out with a brush in the direction of the wood grain. On garden furniture, apply 2 sparing coats.
<b>Renovation of open-pored surfaces</b>	Old paint coatings must be cleaned and sanded. Subsequent treatment has to be done like the initial treatment. Timely renovation requires only an intermediary and/or final coat. Otherwise a complete new start is necessary. Depending on the weather conditions, type of wood, and color chosen, the maximum time for renovation will vary. Wood that comes in contact with water should be treated regularly.
<b>Renovation of closed-pored surfaces</b>	Pore-clogging coatings (oil-based paints, thick-layered coatings, wax coats) must be sanded or stripped until there is no old residue. Follow the instructions for initial treatment and observe the potentially reduced absorbency.
<b>Care</b>	Possible fungal infestations on the surface should be removed. Their appearance depends on the surface roughness, direction, weather side, moisture content, natural cover etc. Clean with GLOUROS Natural Siding and Masonry Cleaner No. 1806 and treat afterwards with KALDET After Care No. 276.
<b>Important tips</b>	When purchasing more than one container of paint, be sure that all containers have the same batch number. Provide enough ventilation during application and drying times.  <b>Seams of new windows</b> should be treated with a single, very thin coat of KALDET All Weather Stain No. 281. Silicone sealant should be applied only after complete drying and should not be painted over with KALDET. Linseed oil based putty can be painted over after one day.  Certain mixed colors with ultramarine blue and country blue, tend to separate the pigments and should therefore be stirred constantly. Repaint 10 minutes after application.  If the stain drips off or bubbles appear during application, an incompatibility exists through the pre-treatment or it has been sanded to smooth. Coarser sanding may possibly create remedy.

These directions are the result of long years of research and practical testing. They are backed by our most current expert information. New findings may invalidate this information. The latest version is available on our website at [www.livos.de](http://www.livos.de). This data sheet is meant to serve as information and instruction. No legal liability should be interpreted from it. In case of doubt, please contact the retailer, wholesaler, or manufacturer.

July 2015